



Specification of Bitumen 100/150

Bitumen 100/150	Test method	Unit	Specification
Penetration @ 25°C	IP 49	mm/1	100/150
Softening point °c	IP 58	°C	39/47
Kinematic Viscosity @ 135°C	IP 370	mm2/s	175 min
Flashpoint °c	IP 36	°C	230 min
Solubility is CS2(wt) %	IP 47	wt %	99 min