

Specificaiton of Bitumen RC70

Penetration 77°f(25°c) 10 0g,5s mm	80	120	ASTM D5
Ductility 77°f(25°c) 5cm/m in cm	100	—	ASTM D113
Solubility in trichloroethylene %	99	—	ASTM D2042
Water, percent volume	—	0.2	ASTM D95