



Specification of Bitumen 20/30

Bitumen 20/30	Test method	Unit	Specification
Penetration @ 25°C	EN 1426	mm/10	20/30
Softening point °C	EN 1427	°C	53/65
Kinematic Viscosity @ 135°C	EN 1259 5	mm ² /s	530 min
Flashpoint °C	EN 2259 2	°C	240 min
Solubility in CS ₂ (wt) %	EN 1259 2	wt %	99 min