

### Specification of bitumen 90/10

<b>BITUMEN 90/10</b>	<b>SPECIFICATION</b>	<b>TEST METHOD ASTM/EN13304</b>
SPECIFIC GRAVITY @ 25/25 CG	1.04	D-70
PENETRATION @ 25 C	12	D-5
SOFTENING POINT C	86	D-36
LOSS ON HEATING(WT) %	0.1	D-6
FLASH POINT C	340	D-92
SOLUBILITY IS CS2(WT) %	99.5	D-4
DUCTILITY @ 25 °C	1.8	1.5 CM MIN
SATURATES (ASTM D2007)	6%	D2007
ASPHALTENES (IP 143)	37%	IP 143
RESINS	28%	D2007
AROMATICS	30%	D2007