

Specification of Bitumen CRMB 60		
CHARACTERISTIC	CRMB 60	TEST METHOD
Penetration at 25°C, 0.1mm, 100g, 5s	< 50	IS 15462-2004
Softening Point (R&B) °C, Min	60	IS 15462-2004
Fraass breaking point, °C, Max	–	IS 15462-2004
Flash Point, COC, °C, Mina	220	IS 15462-2004
Elastic recovery of half thread in ductilometer at 15°C, % Min	50	IS 15462-2004
Separation, difference in softning point, R&B, °C, Max	4	IS 15462-2004
Viscosity at 150°C, Poise	3 to 9	IS 15462-2004
Thin Film Oven Tests and Test on Residue		
(a) Loss in mass, % Max.	1	IS 15462-2004
(b) Increasing in Softning Point, °C, Max	5	IS 15462-2004
(c) Reduction in penetration of residue at 25°C, % Max	40	IS 15462-2004
(d) Elastic recovery of half thread in ductilometer at 25°C, % Min	35	IS 15462-2004