



### Specification of Cutback Asphalt MC 3000

| Properties  | Min  | Max  | Test Method            |
|---|------|------|------------------------|
| Kinemalic 1 viscosity at 60°C, eSt                                  | 3000 | 6000 | ASTM D2170             |
| <a href="#">Flash Point (Tag Open-Cup),°C</a>                       | 66   | –    | ASTM D1310             |
| Distillate test 2 :   |      |      |                        |
| Distillate, percent by Volume of total 360°C                        |      |      |                        |
| To 190°C  | –    | –    | ASTM D402              |
| To 225°C  | –    | –    | ASTM D402              |
| To 260°C  | –    | 15   | ASTM D402              |
| To 316°C  | 80   | –    | ASTM D402              |
| Residue from distillation to 360°C:                                 |      |      |                        |
| Test on residue from distillation Penetration at 25°C, 100g, 5 sec. | 80   | –    |                        |
| Ductility 3 at 25°C, cm   | 120  | 250  | ASTM D402 / ASTM D113  |
| Solubility in trichloroethylene, percent mass                       | 100  | –    | ASTM D402 / ASTM D2024 |
| Water, percent volume   | –    | 0.2  | ASTM D95               |