

Specification of Bitumen Class 170

| Bitumen C170 | Unit | Specification |
|-------------------------------|-------------|----------------------|
| Viscosity at 60°C | Pa.s | 170 |
| Viscosity at 135°C | Pa.s | 0.4 |
| Viscosity at 60°C, after RTFO | Pa.s | 300 |
| Penetration at 25°C | dmm | 70 |
| Flashpoint 60°C | °C | 360 |
| Viscosity of residue at 60°C | original | 180 |
| Flashpoint | °C | 232 min |
| Density at 15°C | Kg/m3 | 1.04 |