

Specification of Anioinc Bitumen Emulsion RS2

PROPERTY	MIN	MAX	TEST METHOD
Saybolt fural Viscosity@ 50 °C (s)	75	400	ASTM D244
Storage stability, 24h (%)		1	ASTM D6930
Particle charge test	Minus		ASTM D244
Demulcibility, 35ml, 8% dioctyl sodium sulfosuccinate, %	60	–	ASTM D6936
Sieve (%)		0.1	ASTM D6933
Residue by distillation (%)	65		ASTM D244
Penetration, 25 °C, 100g, 5Sec	100	200	ASTM D5
Solubility in trichloroethylene %	97.5	–	ASTM D2042
Residue ductility, 25 °C, 5cm/min (cm)	40		ASTM D113