

Specification of Bitumen QS1h

PROPERTY	MIN	MAX	TEST METHOD
Viscosity SSF , 25 °C (s)	20	100	ASTM D244
Viscosity SSF , 50 °C (s)			ASTM D244
Storage stability, 24h (%)			ASTM D6930
Demulcibility , 0.02 N CaCl ₂ (%)			
Cement mixing (%)			
Sieve (%)		0.1	ASTM D6933
Residue by distillation (%)	57		ASTM D244
Residue penetration, 25 °C	40	90	ASTM D5
Residue ductility, 25 °C, 5cm/min (cm)	40		ASTM D113