



Specification of Bitumen RC250			
Properties	Min	Max	Test Method
Kinemalic 1 viscosity at 60°C, eSt	250	500	ASTM D2170
Flash Point (Tag Open-Cup),°C	27	–	ASTM D1310
Distillate test 2 :			
Distillate, percent by Volume of total 360°C			
To 190°C	–	–	ASTM D402
To 225°C	35	–	ASTM D402
To 260°C	60	–	ASTM D402
To 316°C	80	–	ASTM D402
Residue from distillation to 360°C:			
Test on residue from distillation Penetration at	80	120	
25°C,100g, 5 sec.			
Ductility 3 at 25°C, cm	100	–	ASTM D402 / ASTM D113
Solubility in trichloroethylene, percent mass	100	–	ASTM D402 / ASTM D2024
Water, percent volume	–	0.2	ASTM D95