

### Specification of bitumen HFMS2S

PROPERTY	MIN	MAX	TEST METHOD
Viscosity SSF , 25 °C (s)	50	–	ASTM D244
Storage stability, 24h (%)	–	1	ASTM D6930
Particle charge test		Minus	ASTM D244
Sieve (%)	–	0.1	ASTM D6933
Residue by distillation (%)	65	–	ASTM D244
Solvents, by volume of emulsion	1	7	ASTM D6997
Residue penetration, 25 °C	200	–	ASTM D5
Residue ductility, 25 °C, 5cm/min (cm)	40	–	ASTM D113
Solubility in trichloroethylene %	97.5	–	ASTM D2042
Float of residue. 60 °C (s)		1200	ASTM D139