

## Specification of Bitumen HFRS2

PROPERTY	MIN	MAX	TEST METHOD
Viscosity, Saybolt Furol at 25 °C, SFS	20	100	ASTM D244
Storage stability, 24h (%)		1	ASTM D6930
Demulsibility, 35ml, 8% dioctyl sodium sulfosuccinate,	60	–	ASTM D6936
Particle charge test	minus		ASTM D244
Sieve (%)		0.1	ASTM D6933
Residue by distillation (%)	63		ASTM D244
Residue penetration, 25 °C	100	200	ASTM D5
Residue ductility, 25 °C, 5cm/min (cm)	40		ASTM D113
Float of residue. 60 °C (s)	1200		