



Specification of Bitumen MS2h

PROPERTRY	MIN	MAX	TEST METHOD
Viscosity, Saybolt Furol at 25 °C, SFS	20	100	ASTM D244
Storage stability, 24h (%)		1	ASTM D6930
Particle charge test	Minus		ASTM D244
Cement mixing (%)			
Sieve (%)		0.1	ASTM D6933
Residue by distillation (%)	65		ASTM D244
Residue penetration, 25 °C	40	90	ASTM D5
Solubility in trichloroethylene %	97.5		ASTM D2042
Residue ductility, 25 °C, 5cm/min (cm)	40		ASTM D113