

Specification of Bitumen Primer

Bitumen Primer D-41 Specifications		
Property	Specifications	Test Method
Density, Kg/litre	0.85-0.88	ASTM D-70
Saybolt Furol Viscosity at 250C Seconds	25-125	ASTM D-88
Tack Free time, hour	2hrs at 300 C	—
Distillation, Volume% of the Primer		
Up to 2250C	35 (Min)	ASTM D-402
Up to 3600C	65 (Max)	
Tests on residue from distillation:	20-50	ASTM D-5
Penetration at 250C	99	ASTM D
Solubility in trichlorethylene%		2042
Water Content	0.5 (Max)	ASTM D-95